

ACCU-FRETS® fretwire is normally manufactured from a nickel/silver alloy, sometimes called "German silver." The most common combination is an 18% nickel content and the three-quarter hard or harder condition for durability. Dunlop ACCU-FRET fretwire is also available in brass and 18% nickel content in soft condition, and 12% nickel content in both hard and soft conditions, offering a tremendous array of fretwire for luthiers worldwide.



ACCU-FRETS®

ACCU-FRET® TUBES

For the repairman or facility preferring to work with lengths rather than pre-cut material we offer 20 two foot (.609 meter) lengths, straightened.

6T2/(Fret No.) Accu-Fret® Tube


packaged in a cardboard storage tube

ACCU-FRET® SETS

Contains 24 straightened and pre-cut to 2-5/8" (66.67mm) frets. Easy to bend for curved fingerboards.

6S/(Fret No.) Accu Fret® Set

packaged on a blister pack card



FRETWIRE IS ALSO AVAILABLE COILED,
IN LENGTHS, OR BY POUND WEIGHT
(2 LBS. MINIMUM)

	No.	Material	-	A	+	-	B	+	-	C	+	-	D	+	-	E	+		
LARGE OR JUMBO	6000	18% N/S HARD	MM	-0.200	3.250	0.200	-0.150	2.990	0.050	-0.100	0.910	0.050	-0.050	0.530	0.050	-0.075	1.470	0.075	
		IN.	-0.008	0.128	0.008	-0.006	0.118	0.002	-0.004	0.036	0.002	-0.002	0.021	0.002	-0.003	0.058	0.003		
	6100	18% N/S HARD	MM	-0.200	3.180	0.100	-0.150	2.790	0.050	-0.100	0.810	0.050	-0.050	0.530	0.050	-0.075	1.400	0.075	
		IN.	-0.008	0.125	0.004	-0.006	0.110	0.002	-0.004	0.032	0.002	-0.002	0.021	0.002	-0.003	0.055	0.003		
	6105	18% N/S HARD	MM	-0.200	2.990	0.200	-0.150	2.290	0.050	-0.100	0.790	0.050	-0.050	0.530	0.050	-0.075	1.400	0.075	
		IN.	-0.008	0.118	0.008	-0.006	0.090	0.002	-0.004	0.031	0.002	0.002	0.021	0.002	-0.003	0.055	0.003		
	6110	18% N/S HARD	MM	-0.200	2.640	0.100	-0.150	2.920	0.050	-0.100	0.910	0.050	-0.050	0.510	0.050	-0.075	1.270	0.075	
		IN.	-0.008	0.104	0.004	-0.006	0.115	0.002	-0.004	0.036	0.002	-0.002	0.020	0.002	-0.003	0.050	0.003		
	6120	18% N/S HARD	MM	-0.150	3.000	0.150	-0.050	2.900	0.050	-0.050	0.950	0.030	-0.050	0.600	0.050	-0.030	1.300	0.030	
		IN.	-0.006	0.118	0.006	-0.002	0.114	0.002	-0.002	0.037	0.001	-0.002	0.024	0.002	-0.001	0.051	0.001		
	6130	18% N/S HARD	MM	-0.203	2.794	0.203	-0.051	2.692	0.051	-0.076	0.914	0.076	-0.051	0.508	0.051	-0.051	0.914	0.051	
		IN.	-0.008	0.110	0.008	-0.002	0.106	0.002	-0.003	0.036	0.003	-0.002	0.020	0.002	-0.002	0.036	0.002		
MEDIUM OR REGULAR	6140	18% N/S HARD	MM	-0.150	2.800	0.150	-0.050	2.700	0.050	-0.050	0.950	0.050	-0.030	0.600	0.030	-0.050	1.000	0.050	
		IN.	-0.006	0.110	0.006	-0.002	0.106	0.002	-0.002	0.037	0.002	-0.001	0.024	0.001	-0.002	0.039	0.002		
	6150	18% N/S HARD	MM	-0.200	2.743	0.100	-0.150	2.591	0.050	-0.100	0.787	0.050	-0.050	0.510	0.050	-0.075	1.067	0.075	
		IN.	-0.008	0.108	0.004	-0.006	0.102	0.002	-0.004	0.031	0.002	-0.002	0.020	0.002	-0.003	0.042	0.003		
	6155	18% N/S SOFT	MM	-0.203	2.870	0.203	-0.051	2.616	0.051	-0.076	0.787	0.076	-0.051	0.533	0.051	-0.051	1.168	0.051	
		IN.	-0.008	0.113	0.008	-0.002	0.103	0.002	-0.003	0.031	0.003	-0.002	0.021	0.002	-0.002	0.046	0.002		
	6160	18% N/S SOFT	MM	-0.150	2.800	0.150	-0.050	2.700	0.050	-0.050	0.950	0.050	-0.040	0.600	0.040	-0.050	1.000	0.050	
		IN.	-0.006	0.110	0.006	-0.002	0.106	0.002	-0.002	0.037	0.002	-0.002	0.024	0.002	-0.002	0.039	0.002		
	6170	12% N/S HARD	MM	-0.250	3.280	0.250	-0.020	2.500	0.100	-0.250	1.220	0.260	-0.030	0.600	0.020	-0.050	1.100	0.050	
		IN.	-0.010	0.129	0.010	-0.001	0.099	0.004	-0.010	0.048	0.010	-0.001	0.024	0.001	-0.002	0.043	0.002		
	SMALL	6180	BRASS	MM	-0.250	2.570	0.250	-0.240	2.720	0.100	-0.250	0.890	0.250	-0.030	0.500	0.180	-0.050	1.100	0.050
			IN.	-0.010	0.101	0.010	-0.009	0.107	0.004	-0.010	0.035	0.010	-0.001	0.020	0.007	-0.002	0.043	0.002	
6190		18% N/S HARD	MM	-0.210	2.390	0.200	-0.050	2.130	0.050	-0.080	0.740	0.070	-0.050	0.510	0.050	-0.050	0.990	0.050	
		IN.	-0.008	0.094	0.008	-0.002	0.084	0.002	-0.003	0.029	0.003	-0.002	0.020	0.002	-0.002	0.039	0.002		
6200		12% N/S HARD	MM	-0.260	2.540	0.280	-0.020	2.000	0.100	-0.250	1.140	0.260	-0.030	0.600	0.020	-0.100	1.100	0.050	
		IN.	-0.010	0.100	0.011	-0.001	0.079	0.004	-0.010	0.045	0.010	-0.001	0.024	0.001	-0.004	0.043	0.002		
6210		12% N/S SOFT	MM	-0.250	2.540	0.250	-0.050	2.000	0.150	-0.270	0.860	0.250	-0.040	0.500	0.040	-0.050	1.100	0.050	
		IN.	-0.010	0.100	0.010	-0.002	0.079	0.006	-0.011	0.034	0.010	-0.002	0.020	0.002	-0.002	0.043	0.002		
6220		12% N/S HARD	MM	-0.250	2.400	0.250	-0.020	2.000	0.080	-0.250	0.960	0.250	-0.040	0.500	0.040	-0.050	1.100	0.050	
		IN.	-0.010	0.097	0.010	-0.001	0.079	0.003	-0.010	0.038	0.010	-0.002	0.020	0.002	-0.002	0.043	0.002		
6230		18% N/S HARD	MM	-0.260	2.480	0.240	-0.010	1.990	0.100	-0.100	0.900	0.100	-0.060	0.520	0.020	-0.005	1.080	0.070	
		IN.	-0.010	0.098	0.009	0.001	0.078	0.004	-0.004	0.035	0.004	-0.002	0.020	0.001	-0.002	0.043	0.003		
6240	18% N/S HARD	MM	-0.203	2.388	0.203	-0.051	2.032	0.051	-0.076	0.787	0.076	-0.051	0.483	0.051	-0.051	0.940	0.051		
	IN.	-0.008	0.094	0.008	-0.002	0.080	0.002	-0.003	0.031	0.003	-0.002	0.019	0.002	-0.002	0.037	0.002			
6250	18% N/S HARD	MM	-0.203	2.413	0.203	-0.051	1.905	0.051	-0.076	0.914	0.076	-0.051	0.508	0.051	-0.051	0.762	0.051		
	IN.	-0.008	0.095	0.008	-0.002	0.075	0.002	-0.003	0.036	0.003	-0.002	0.020	0.002	-0.002	0.030	0.002			
6260	18% N/S HARD	MM	-0.150	2.800	0.150	-0.100	2.000	0.100	-0.050	0.950	0.050	-0.050	0.600	0.050	-0.030	1.000	0.030		
	IN.	-0.006	0.110	0.006	-0.004	0.079	0.004	-0.002	0.037	0.002	-0.002	0.024	0.002	-0.001	0.039	0.001			
6265	18% N/S SOFT	MM	-0.150	2.800	0.150	-0.100	2.000	0.100	-0.050	0.950	0.050	-0.050	0.600	0.050	-0.030	1.000	0.030		
	IN.	-0.006	0.110	0.006	-0.004	0.079	0.004	-0.002	0.037	0.002	-0.002	0.024	0.002	-0.001	0.039	0.001			
6270	18% N/S HARD	MM	-0.203	2.540	0.203	-0.051	1.905	0.051	-0.076	0.914	0.076	-0.051	0.508	0.051	-0.051	0.762	0.051		
	IN.	-0.008	0.100	0.008	-0.002	0.075	0.002	-0.003	0.036	0.003	-0.002	0.020	0.002	-0.002	0.030	0.002			
6290	18% N/S HARD	MM	-0.203	2.337	0.203	-0.051	1.981	0.051	-0.076	0.787	0.076	-0.051	0.508	0.051	-0.051	1.016	0.051		
	IN.	-0.008	0.092	0.008	-0.002	0.078	0.002	-0.003	0.031	0.003	-0.002	0.020	0.002	-0.002	0.040	0.002			
FLAT	6300	12% N/S HARD	MM	-0.250	1.940	0.250	-0.020	1.600	0.120	-0.250	0.960	0.250	-0.030	0.600	0.020	-0.140	0.640	0.060	
		IN.	-0.010	0.076	0.010	-0.001	0.063	0.005	-0.010	0.038	0.010	-0.001	0.024	0.001	-0.006	0.025	0.002		
	6310	18% N/S HARD	MM	-0.203	2.311	0.203	-0.051	1.346	0.051	-0.076	0.940	0.076	-0.051	0.559	0.051	-0.051	0.787	0.051	
		IN.	-0.008	0.091	0.008	-0.002	0.053	0.002	-0.003	0.037	0.003	-0.002	0.022	0.002	-0.002	0.031	0.002		
	6320	18% N/S HARD	MM	-0.203	2.159	0.203	-0.051	1.194	0.051	-0.076	0.711	0.076	-0.051	0.533	0.051	-0.051	0.737	0.051	
		IN.	-0.008	0.085	0.008	-0.002	0.047	0.002	-0.003	0.028	0.003	-0.002	0.021	0.002	-0.002	0.029	0.002		
	6330	18% N/S HARD	MM	-0.203	2.388	0.203	-0.051	1.092	0.051	-0.076	0.787	0.076	-0.051	0.508	0.051	-0.051	0.787	0.051	
		IN.	-0.008	0.094	0.008	-0.002	0.043	0.002	-0.003	0.031	0.003	-0.002	0.020	0.002	-0.002	0.031	0.002		
	6340	18% N/S HARD	MM	-0.254	2.235	0.254	-0.533	1.829	0.381	-0.254	0.838	0.254	-0.127	0.508	0.102	-0.127	0.889	0.127	
		IN.	-0.010	0.088	0.010	-0.021	0.072	0.015	-0.010	0.033	0.010	-0.005	0.020	0.004	-0.005	0.035	0.005		

STANDARD APPLICATIONS

- 6105 MAXIMUM HEIGHT, NARROWER
- 6230 FENDER GUITARS
- 6170 OVERSIZED FRET SLOTS
- 6130 GIBSON GUITARS ("JUMBO" WIRE)
- 6280, 6290 BANJO
- 6230 MARTIN GUITARS
- 6110 BASS
- 6000, 6100, 6110 MAXIMUM MASS